# Formulating a Greener World®

# SoluJET® 2720B

Solvent ink for penetrable media















#### TECHNICAL DATA SHEET

SoluJET® 2720B blue solvent TIJ 2.5 ink is designed for penetrating into penetrable substrates such as polyvinyl chloride, polycarbonate, polyurethane, acrylic coating resulting permanent printouts.

SoluJET® 2720B ink provides fast penetrating, excellent scratch resistance and chemical resistance, long decap time and high optical density. (1)

#### **Technical Specifications**

<del>-</del>	
	SoluJET® 2720B Print Cartridge
Ink type	Blue dye solvent ink
Print cartridge type	HP 45si
Resolution	Up to 600 dpi, recommended $300 \times 300$ dpi
Nozzle count	300
Print swath	12.7 mm
Firing voltage	9.0 V
Fire pulse width	2.2 μs
Pulse warming	OFF
Decap time(1)	30 min
Drying time <sup>(1)</sup>	8 - 10 s on rigid PVC pipe at $300 \times 300$ dpi
Throw distance <sup>(2)</sup>	Up to 5 mm, recommended 3 mm
Average delivered ink	36 mL (vertical)
Average drop volume	36 pL
Operating conditions	15 °C to 35 °C, 35% to 80% RH
Shipping / storage temperature	5 °C to 30 °C
Best before <sup>(3)</sup>	4 months from filling date
	C

#### **Cartridge Shipping & Storage**

- The cartridge should be stored in vacuum sealed pouch until used.
- Use the cartridge within two weeks of removing it from vacuum sealed pouch for best performance.
- Store the cartridge with a clip placed over the printhead. Nozzles up or horizontal.
- Refer to Safety Data Sheet for more information.

## Cartridge Maintenance & Handling

- Use a lint-free cloth moistened with ethanol (> 98%) to clean the cartridge printhead.
- Holding the cartridge printhead face down, gently press the printhead on a lint-free cloth to allow ink to wick out. Then, slowly and lightly wipe across the tip of the long edge.
- Do not shake the cartridge.

## **Ordering Information**

Product number	Product description
2720B42A	SoluJET® 2720B Print Cartridge

<sup>(1)</sup> Ink performance may vary depending on substrate, printer, and environmental conditions.

#### **MYLAN GROUP**

Longduc Industrial Park, Travinh City, Travinh Province, Vietnam

Tel.: +84 294 3846 997 - Fax: +84 294 3846 998

Email: inks@mylangroup.com Website: www.mylangroup.com

<sup>(2)</sup> Recommended. May vary by application.

<sup>(3)</sup> Must be shipped and stored under recommended conditions.